

PVC MASTERBATCHES

Properties	Colour	Hardness	Specific Gravity	Thermal Stability @ 200°C	Volume Resistivity @ 27°C	Tensile Strength	Elongation
Test Method		DIN 5305	ASTM D792		ASTMD257	IS:10810	IS:10810
Units		Shore A		Minutes	x10 ¹³ Ohm. Cm	Kg/cm ²	%
MASTERBATCHES							
BMS	Black	70	1.35	80	1.0	150	200
WMS	White - Natural, Egg	75	1.5	80	1.0	150	200
GRMS	Grey - Light, Dark, Intermediate	75	1.45	80	1.0	150	200
PMS	Pink	75	1.45	80	1.0	150	200
VMS	Violet	75	1.45	80	5.0	150	200
TMS	Tan	75	1.45	80	1.0	150	200
BLMS	Blue	75	1.45	80	1.0	150	200
GMS	Green	75	1.45	80	1.0	150	200
YMS	Yellow	75	1.45	80	5.0	150	200
OMS	Orange	75	1.45	80	1.0	150	200
RMS	Red - Blood, Postal	75	1.45	80	1.0	150	200
BRMS	Brown	75	1.45	80	1.0	150	200
MRMS	Maroon	75	1.45	80	1.0	150	200



kadakia plastics & chemicals pvt. ltd.
47-A, Nandjyot Ind. Estate, Andheri-Kurla Road, Mumbai 400 072.

Tel.: +91 (22) 2851 6621 • Fax : +91 (22) 2851 6626
E-mail: info@kadakioplastics.com
website: www.kadakioplastics.com